

In the Claims:

1. **(original)** A process for the production of a strongly adherent coating on an inorganic or organic metalized substrate, wherein

- a) a low-temperature plasma treatment, a corona discharge treatment or a flame treatment is carried out on the inorganic or organic substrate,
- b) one or more photoinitiators or mixtures of photoinitiators with monomers or/and oligomers, containing at least one ethylenically unsaturated group, or solutions, suspensions or emulsions of the afore-mentioned substances, are applied to the inorganic or organic metalized substrate, and
- c) using suitable methods those afore-mentioned substances are optionally dried and/or are irradiated with electromagnetic waves.

2. **(original)** A process for the production of a strongly adherent coating on an inorganic or organic metalized substrate, wherein

- a) a low temperature plasma treatment, a corona discharge treatment or a flame treatment is carried out on the inorganic or organic metalized substrate,
- b) one or more photoinitiators or mixtures of photoinitiators with monomers or/and oligomers, containing at least one ethylenically unsaturated group, or solutions, suspensions or emulsions of the afore-mentioned substances, are applied to the inorganic or organic metalized substrate,
- c) using suitable methods those afore-mentioned substances are dried and/or irradiated with electromagnetic waves and either
 - d1) the substrate so precoated with photoinitiator is coated with a composition comprising at least one ethylenically unsaturated monomer or oligomer, and the coating is cured by means of UV/VIS radiation or an electron beam; or
 - d2) the substrate so precoated with photoinitiator is coated with a printing ink and dried.

3. **(original)** A process according to claim 1, wherein the photoinitiator is a compound or combination of compounds from the classes of benzoines, benzil ketals, acetophenones, hydroxyalkylphenones, aminoalkylphenones, acylphosphine oxides, acylphosphine sulfides, acyloxyiminoketones, peroxyketone compounds, halogenated acetophenones, phenylglyoxalates, dimeric phenylglyoxalates, benzophenones, oximes and oxime esters, thioxanthenes, thiazolines, ferrocenes, coumarins, dinitrile compounds, titanocenes, sulfonium salts, iodonium salts, diazonium salts, onium salts, borates, triazines, bisimidazoles, polysilanes and dyes, and also corresponding coinitiators and/or sensitizers.

4. **(original)** A process according to claim 1, wherein the photoinitiator is a compound of formula I or Ia



wherein

(IN) is a photoinitiator base structure;


A is a spacer group or a single bond;

(RG) is hydrogen or at least one functional ethylenically unsaturated group; and


(RG') is a single bond or a divalent radical that contains at least one functional ethylenically unsaturated group, or is a trivalent radical.

5. **(original)** A process according to claim 4, wherein in the compound of formula I or Ia

(IN) is a photoinitiator base structure of formula (II) or (III)




(II),




(III),

R₁ is a group (A), (B), (C) or (III)



(A),

-CR₆R₇R₈ (B)







n is a number from 0 to 6;

R₂ is hydrogen, C₁-C₁₂alkyl, halogen, the group (RG)-A- or, when R₁ is a group (A), two radicals

R₂ in the ortho-position to the carbonyl group may also together be -S- or ;

R₃ and **R₄** are each independently of the other C₁-C₆alkyl, C₁-C₆alkanoyl, phenyl or benzoyl, the radicals phenyl and benzoyl each being unsubstituted or substituted by halogen, C₁-C₆alkyl, C₁-C₆alkylthio or by C₁-C₆alkoxy;

R₅ is hydrogen, halogen, C₁-C₁₂alkyl or C₁-C₁₂alkoxy or the group (RG)-A- ;

R_6 is OR_9 or $N(R_9)_2$ or is , , ,  or SO_2R_9 ;

R_7 and R_8 are each independently of the other hydrogen, C_1 - C_{12} alkyl, C_2 - C_{12} alkenyl, C_1 - C_{12} alkoxy, phenyl or benzyl or R_7 and R_8 together are C_2 - C_6 alkylene;



R_9 is hydrogen, C_1 - C_6 alkyl or C_1 - C_6 alkanoyl;

R_{10} is hydrogen, C_1 - C_{12} alkyl or phenyl;

R_{11} is hydrogen, C_1 - C_4 alkyl or ; and

X_1 is oxygen or sulfur.

6. (currently amended) A process according to claim 5, wherein in the compound of formula I or Ia
(RG) is $R_cR_bC=CR_a$;

(RG') is  or , and

R_a , R_b and R_c are each independently of the other hydrogen or C_1 - C_6 alkyl, ~~especially hydrogen or methyl.~~

7. (currently amended) A process according to ~~any one of the preceding claims 1 to 6~~ claim 1, wherein the photoinitiator(s) or mixtures thereof with monomers or oligomers are used in combination with one or more liquids ~~(such as solvents or water)~~ in the form of solutions, suspensions and emulsions.

8. (original) A process according to claim 2, wherein in process step d1) a photopolymerisable composition, comprising at least one ethylenically unsaturated monomer or/and oligomer and at least one photoinitiator and/or coinitiator, is applied to the pretreated substrate and cured by means of UV/VIS radiation.

9. (currently amended) A process according to ~~either claim 1 or claim 2~~, wherein an inert gas or a mixture of inert gas with reactive gas is used as the plasma gas.

10. **(original)** A process according to claim 9, wherein air, H₂, CO₂, He, Ar, Kr, Xe, N₂, O₂ or H₂O are used singly or in the form of a mixture.

11. **(currently amended)** A process according to ~~either claim 1 or claim 2~~, wherein the photoinitiator layer applied has a layer thickness of up to 500 nm, ~~especially ranging from a monomolecular layer up to 200 nm.~~

12. **(currently amended)** A process according to ~~either claim 1 or claim 2~~, wherein process step b) is carried out immediately after process step a) or within 24 hours after process step a).

13. **(currently amended)** A process according to ~~either claim 1 or claim 2~~, wherein the concentration of photoinitiator or photoinitiators in process step b) is from 0.01 to 99.5 %, ~~preferably from 0.1 to 80 %.~~

14. **(currently amended)** A process according to ~~either claim 1 or claim 2~~, wherein process step c) is carried out immediately after process step b) or within 24 hours after process step b).

15. **(currently amended)** A process according to ~~either claim 1 or claim 2~~, wherein drying in process step c) is effected in ovens, with hot gases, heated rollers or IR or microwave radiators or by absorption.

16. **(currently amended)** A process according to ~~either claim 1 or claim 2~~, wherein irradiation in ~~b)~~ process step c) is effected with a source that emits electromagnetic waves of wavelengths in the range from 200 nm to 700 nm, or by electron beams.

17. **(original)** A process according to claim 1, wherein portions of the photoinitiators, or mixtures thereof with monomers and/or oligomers, applied in process step b) that have not been crosslinked after irradiation in process step c) are removed by treatment with a solvent and/or water and/or mechanically.

18. **(original)** A process according to claim 2, wherein after irradiation in process step d1) portions of the coating are removed by treatment with a solvent and/or water and/or mechanically.

19. **(cancelled)**

20. **(currently amended)** A strongly adherent coating on an inorganic or organic metalized substrate obtained ~~able~~ by a process according to ~~any one of the preceding claims 1 to 18~~ claim 1.

21. **(new)** A strongly adherent coating on an inorganic or organic metalized substrate obtained by a process according to claim 2.